



柳桥集团

声誉卓越的羽绒专家

羽毛绒检测报告单

Feather and Down Test Report

长白山白鹅绒

CONTENT IDFB Part 3 2013

朵绒 Down Clusters	92.7%
绒丝 Down Fibers	1.6%
羽丝 Waterfowl Feather Fibers	1.0%
毛片 Waterfowl Feathers	4.5%
损伤羽毛 Broken and Damaged Waterfowl Feathers	0.0%
长毛片 Quill	0.0%
陆禽毛 Landfowl	0.1%
杂质 Residue	0.1%
总计 Total	100%

蓬松度 Steam Fill Power IDFB Part 10 -B 2015

Volume 812in³ /30g

耗氧指数 Oxygen IDFB Part 7 2013

耗氧指数 Oxygen 1.6 mg/100g

清洁度 Turbidity IDFB Part 11 2013

浊度玻璃管 Turbidity Glass Tube 1000mm

残值率 Fat and Oil IDFB Part 4 2013

残值率 Fat and Oil 0.6%

APEO ISO 18254-1 2016

Octylphenol Polyethoxylate (OPEO)	2.3
Nonylphenol Polyethoxylate (NPEO)	3.1
SUM (OPEO+NPEO)	5.4

编制: (Compile) 孙冬敏

校核: (Checked by) 裴伟娟

批准: (Approval) 裴伟娟

编制日期: (Compile Date)

校准日期: (Check Date)

批准日期: (Approval Date)

