



柳桥集团

声誉卓越的羽绒专家

羽毛绒检测报告单

Feather and Down Test Report

广西绿头灰鸭绒

CONTENT IDFB Part 3 2013

朵绒 Down Clusters	91.6%
绒丝 Down Fibers	1.4%
羽丝 Waterfowl Feather Fibers	1.9%
毛片 Waterfowl Feathers	4.3%
损伤羽毛 Broken and Damaged Waterfowl Feathers	0.1%
长毛片 Quill	0.0%
陆禽毛 Landfowl	0.2%
杂质 Residue	0.5%
总计 Total	100%

蓬松度 Steam Fill Power IDFB Part 10 -B 2015

Volume 805 in³/30g

耗氧指数 Oxygen IDFB Part 7 2013

耗氧指数 Oxygen 1.6 mg/100g

清洁度 Turbidity IDFB Part 11 2013

浊度玻璃管 Turbidity Glass Tube 1000mm

残值率 Fat and Oil IDFB Part 4 2013

残值率 Fat and Oil 0.7%

APEO ISO 18254-1 2016

Octylphenol Polyethoxylate (OPEO)	1.1
Nonylphenol Polyethoxylate (NPEO)	1.2
SUM (OPEO+NPEO)	2.3

编制: (Compile)

孙冬敏

校核: (Checked by)

裴伟娟

批准: (Approval)



编制日期: (Compile Date)

校准日期: (Check Date)

批准日期: (Approval Date)