



柳桥集团

声誉卓越的羽绒专家

羽毛绒检测报告单

Feather and Down Test Report

西伯利亚冰原白鹅绒

CONTENT IDFB Part 3 2013	
朵绒 Down Clusters	92.4%
绒丝 Down Fibers	2.4%
羽丝 Waterfowl Feather Fibers	1.2%
毛片 Waterfowl Feathers	3.7%
损伤羽毛 Broken and Damaged Waterfowl Feathers	0.1%
长毛片 Quill	0.0%
陆禽毛 Landfowl	0.0%
杂质 Residue	0.2%
总计 Total	100%
蓬松度 Steam Fill Power IDFB Part 10 -B 2015	
Volume	815in ³ /30g
耗氧指数 Oxygen IDFB Part 7 2013	
耗氧指数 Oxygen	1.6 mg/100g
清洁度 Turbidity IDFB Part 11 2013	
浊度玻璃管 Turbidity Glass Tube	1000mm
残值率 Fat and Oil IDFB Part 4 2013	
残值率 Fat and Oil	0.6%
APEO ISO 18254-1 2016	
Octylphenol Polyethoxylate (OPEO)	1.2
Nonylphenol Polyethoxylate (NPEO)	1.3
SUM (OPEO+NPEO)	2.5

编制: (Compile)

校核: (Checked by)

批准: (Approval)

编制日期: (Compile Date)

校准日期: (Check Date)

批准日期: (Approval Date)

